

Melbourne Branch:
15 Beverage Dr,
Tullamarine, 3043
Victoria, Australia
P.O. Box 3272
Caroline Springs VIC 3023
Phone: 03 9310 3892
Fax: 03 9338 0924
Email: sales@davmarindustries.com.au



Sydney Branch:
11/30 Barry Road
Chipping Norton 2170
New South Wales, Australia
P.O. Box 3277
Lansvale NSW 2166
Phone: 02 9755 0716
Fax: 02 9755 0715
Email: sydney@davmarindustries.com.au

ABN 56 122 012 202

ACN 122 012 202

Specification Report: Scaffold-mesh

Weight: 80gsm +/- 5%

Construction: HDPE Knitted Yarn

UV Inhibitor – 3%

Testing Method: AS 2001.2.10-1986 (Tear Resistance)

Wing Rip

Test Result: Length: 85.1 N

Width: 62.9 N

Testing Method: AS 2001.2.3.2-2001 (Breaking force of Textile Fabric)

Grab Test

Gauge Length: 75mm

Speed: 300mm/min

Test Result: Length: 450 N

Width: 331 N

Testing Method: AS 2001.2.4-1990 (Bursting Pressure of Textile Fabric)

Method B – Hydraulic Diaphragm Method

Test Result: 1180 Kpa

Testing Method: AS 2001.2.19-1988 (Bursting Force)

Steel Ball Diameter: 25.4mm

Test Result:

Mean: 637 N

Test in Dry State